

## Data Sheet

# Ticuni® - 60

### Description:

A high-purity Active Brazing Filler in composite form containing titanium, copper and nickel, developed for direct application to ceramic surfaces. Nominal composition by weight: **60% Ti, 15% Cu, and 25% Ni**

### Prime features:

- Wets and bonds to virtually any metallic surface, as well as to non-metallics such as oxides, nitrides and carbides
- Allows ceramic-to-ceramic and ceramic-to-metal surfaces to be brazed without metallizing, firing and electroplating
- Cuts time and costs in manufacture of ceramic/metal assemblies
- Produces strong, highly reliable and vacuum-tight brazed joints

### Typical applications:

- One step bonding to ceramics

### Suggested base materials:

- Copper, Kovar, Nickel, Tool/high speed steel, Stainless steel, Ni-super alloys, Titanium, Ceramics, Graphite, Diamond

### Physical Properties\*

|  |                        |
|--|------------------------|
| Liquidus Temperature                   | 940 °C<br>1725 °F      |
| Solidus Temperature                    | 890 °C<br>1635 °F      |
| Coefficient of Thermal Expansion (CTE) |                        |
| Thermal Conductivity (Calculated)      |                        |
| Density                                |                        |
| Yield Strength (0.2% offset)           |                        |
| Tensile Strength                       |                        |
| Elongation (2in/50mm gage section)     |                        |
| Electrical Resistivity                 |                        |
| Electrical Conductivity                |                        |
| Vapor Pressure (Calculated)            |                        |
| Recommended Brazing Temperatures       | 960 - 1100 °C          |
| Recommended Brazing Atmospheres        | 10 <sup>-5</sup> mm Hg |

\* Please note that all values quoted are based on test pieces and may vary according to component design. These values are not guaranteed in any way and should only be treated as indicative values. They should be used for guidance only and for no other purpose whatsoever.

### Impurity Limits

|    |                  |
|----|------------------|
| Zn | less than 0.001% |
| Cd | less than 0.001% |
| Pb | less than 0.002% |
| P  | less than 0.002% |
| C  | less than 0.01%  |

All other metallic impurities having a vapor pressure higher than 10<sup>-7</sup> mm Hg at 500 °C are limited to 0.002% each. Impurities having a vapor pressure lower than 10<sup>-7</sup> mm Hg at 500 °C are limited to a total of 0.075%. (This applies to all forms except powder and extrudable paste.)

### Supplied as:

- Foil
- Paste

The determination as to the adaptability of any Wesgo materials to the specific needs of the Buyer is solely the Buyer's prerogative and responsibility. All technical information, data and recommendations are based on tests and accumulated experience data, which Wesgo believed to be reliable. However, the accuracy and completeness thereof are not guaranteed.



www.morganbrazealloys.com  
 Morgan Advanced Materials, 2425 Whipple Road, Hayward CA 94544  
 Contact: +1 510 491 1100 | Certifications: AS9100D, ISO9001:2015, ISO14001:2015

